

IRON OXIDES

ΛΙΟΚΑ
MAXIM
SM

IMPORT | EXPORT | EMPOWER

“A GLOBAL DISTRIBUTION HUB”


SYNTHETIC IRON OXIDE – BLACK

Product Description


Synthetic iron oxide pigments are globally renowned as one of the most favored coloring agents. They are versatile and well-suited for an array of applications.

Black Oxide

AIO 5799



AIO 330



Applications

Paints | Wood Coatings | Plastic Application | Industry Coating |
Print ink | Art coatings | Powder coating | Cement Colors |
Paver Blocks | Concrete & mortar Colors | Construction Flooring

Technical Index: Black 5799



Properties	Unit	values
Physical Form		Fine Powder.
Chemical Composition		Fe_3O_4
Purity	%	90 % +
Oil Absorption	gm/100gm	20.0 gm/100 gms
Sieve Residue on 325#	%	≤ 0.3
Moisture	%	≤ 0.1 %
pH value		6.8
Hegman		3.0+
Bulk Density	Gm/cm3	5
Specific Gravity	Gm/cm3	5.0
Packaging		25 kgs. Paper Bag
Transport and Storage.		Store in dry place
Safety	.	The product is not classified as Hazardous.

Technical Index: Black 330



Properties	Unit	values
Physical Form		Fine Powder.
Chemical Composition		Fe ₃ O ₄
Purity	%	90 % +
Oil Absorption	gm/100gm	15-25 gm/100 gms
Sieve Residue on 325#	%	≤ 0.5
Moisture	%	≤ 1.5 %
pH value		5-8
Hegman		3.0+
Bulk Density	Gm/cm ³	0.8-1.2
Specific Gravity	Gm/cm ³	4.8
Packaging		25 kgs. Paper Bag
Transport and Storage.		Store in dry place
Safety	.	The product is not classified as Hazardous.

MICRONISED IRON OXIDE – BLACK

Product Description

Synthetic iron oxide pigments are globally renowned as one of the most favored coloring agents. They are versatile and well-suited for an array of applications.

Black Oxide

AIO 330M



Applications

Paints | Wood Coatings | Plastic Application | Industry Coating |
Print ink | Art coatings | Powder coating | Cement Colors |
Paver Blocks | Concrete & mortar Colors | Construction Flooring

Technical Index: Black 330M



Properties	Unit	values
Physical Form		Fine Powder.
Chemical Composition		Fe ₃ O ₄
Purity	%	90 % +
Oil Absorption	gm/100gm	15-25 gm/100 gms
Sieve Residue on 325#	%	≤ 0.01
Moisture	%	≤ 1.0 %
pH value		5-8
Hegman		6.0+
Packaging		25 kgs. Paper Bag
Transport and Storage.		Store in dry place
Safety		The product is not classified as Hazardous.

HEAT STABLE IRON OXIDE – BLACK

Product Description

Synthetic iron oxide pigments are globally renowned as one of the most favored coloring agents. They are versatile and well-suited for an array of applications.

Black Oxide

AIO 304HT



AIO 305HT



Applications

Masterbatch, Plastics, Outdoor Applications (UV resistance)

Technical Index: Black 304HT   | **Black 305HT**  

Properties	Unit	values
Chemical Composition		(Fe,Mn) ₂ O ₃
Oil Absorption	gm/100gm	15-25 gm/100 gms
Sieve Residue on 325#	%	≤ 0.05
Water Soluble Salts(%)	%	≤ 0.5
pH value		5-8
Moisture	%	≤ 1.0 %
Hegman		4.0+
DE		≤ 1.0
Tinting Strength		95-105
Packaging		25 kgs. Paper Bag
Transport and Storage.		Store in dry place
Safety	.	The product is not classified as Hazardous.

GRANULAR IRON OXIDE – BLACK

Product Description

Synthetic iron oxide pigments are globally renowned as one of the most favored coloring agents. They are versatile and well-suited for an array of applications.

Black Oxide

AIO 8330G



Applications

Roof tiles | Pavers and Blocks | Asphalt | Ready - mix/Precast Concrete | Motar, Colored plaster

Technical Index: Black 8330G




Properties	Unit	values
Chemical Composition		Fe ₃ O ₄
Water Absorption	gm/100gm	25-35 gm/100 gms
Matter volatile at 105°C	%	≤ 1.0
Water Soluble Salts(%)	%	≤ 3.0
pH value		5-8
Avg. granular size(mm)		0.3
DE		≤ 1.5
Tinting Strength		95-105
Packaging		25 kgs. Paper Bag
Transport and Storage.		Store in dry place
Safety	.	The product is not classified as Hazardous.

Package:

25kg/paper bags, Polythene bags

500kg/900kg/1000kg super bags

20-22mt/20'FCL with pallets wrapped and shrink



AIOKA

SM
SM
SM

IMPORT | EXPORT | EMPOWER

Add : 402 - Aaron Spectra, Rajpath Rangoli road,
Behind Rajpath Club, Ahmedabad, 380054

Phone : +91 9106314130, +918320126298

Mobile : +91 9725947078, +919727347878

Web : www.aiokasm.com

mail id : shivangi@aiokasm.com
manthan@aiokasm.com